



Argyle | materials inc.

Argyle Materials PCABS10 DATASHEET

January 7, 2020

Tensile Modulus	1830 MPa	ASTM D638
Tensile Strength	35 MPa	ASTM D638
Impact Strength (un-notched)	645 J/m	ASTM D256
Flex Modulus	1860 MPa	ASTM D790
Flex Strength	50 MPa	ASTM D790
Heat deflection @ 66psi	110 C	ASTM D648

Note: these are typical properties to be expected from a fused deposition fabricated test dog bones, provided by third party. Molded pcabs results will differ.

